



SERVICE 24/7 NO VOICE MAIL  
Every Minute, Every Hour, Every Day

# PRIMATOP - HDPE 003955BAS

## Hexene Copolymer

### Features

Excellent stiffness  
Stress crack resistance properties  
Antistat

### Applications

Blow molding  
Sheet extrusion thermofolding

Properties	ASTM	Typical Values
Melt Index	D 1238	0.35
Density	D 1505	0.955
Environmental Stress Crack Resistance (ESCR)		
Condition A, F 50 (100% Igepal)	D 1693	45
Condition B, F 50	D 1693	35
Tensile Yield Strength	D 638	
2" (50 mm) per min.	Type IV	psi 4000
Ultimate Elongation	D 638	
2" (50 mm) per min.	Type IV	> 600 %
Brittleness Temperature	D 746	< -180° F
Flexural Modulus	D 790	psi 200,000

Typical Values represent average laboratory values and are intended as guides only, not as specifications. Properties designated have been determined in accordance with the current issues of the specified testing methods. Methods of American Society for Testing of Materials (ASTM) are used wherever applicable.

A-ToP POLYMERS materials are not designed or manufactured for use in implantation in the human body or in contact with internal body fluids or tissues and should not be used in these applications. A-ToP POLYMERS makes no representation, promise, express warranty or implied warranty concerning the suitability of these materials for use in implantation in the human body or in contact with internal body tissues or fluids.

To the best of our knowledge the information contained herein is accurate. However, neither A-ToP POLYMERS, Inc., nor any of its affiliates assumes liability whatsoever for the accuracy or completeness of the information contained herein. Final determination of the suitability of any information or material for the use contemplated, the manner of use, and whether there is any infringement of patents is the sole responsibility of the user. The above information gives the typical properties only and is not to be used for specification purposes.

47 Rockingham Road, Windham, NH 03087-1307 \* Phone: (603)893-4366 \* Fax: (603)890-1323

[www.a-toppolymers.com](http://www.a-toppolymers.com)

Revised 2/27/07